

# Corres. and Mail BOX AF

AF / 1713

\$11/h

### THE TITLE STATES PATENT AND TRADEMARK OFFICE

In re the Application of: Noriko SAKASHITA et al.

Group Art Unit: 1713

Serial No. 309/530,202

Examiner: Kelechi Chidi Egwim

Filed: April 26, 2000

For. PROCESSING AID FOR VINYL CHLORIDE RESIN AND VINYL CHLORIDE RESIN COMPOSITION

## RESPONSE UNDER 37 C.F.R. §1.116 - EXPEDITED RESPONSE GROUP ART UNIT 1713

#### **BOX AF**

Commissioner for Patents Washington, D.C. 20231

Date: September 10, 2002

Sir:

In response to the Office Action dated June 10, 2002, please amend the above-identified application as follows:

#### **IN THE CLAIMS:**

#### Please amend claim 1 as follows:

1. (Amended) A processing aid for a vinyl chloride resin having specific viscosity  $\eta_{sp}$  of at least 0.5,

which is obtained by polymerizing

1 to 50 parts by weight of a monomer mixture (B) comprising 0 to 49% by weight of methyl methacrylate,

51 to 100% by weight of at least one monomer selected from the group consisting of a methacrylate ester except methyl methacrylate and an acrylate ester, and

0 to 20 % by weight of a vinyl monomer copolymerizable therewith, in the presence of a latex of a (co)polymer having specific viscosity of at least  $\eta_{sp}$  0.7,

By: Noriko SAKASHITA et al. Serial No. 09/530,202

Group Art Unit: 1713
Examiner: Keleghi Chidi Egwim

which is obtained by polymerizing in emulsion 99 to 50 parts by weight of a monomer mixture (A) comprising

51 to 100% by weight of methyl methacrylate,

0 to 49 % by weight of at least one monomer selected from the group consisting of a methacrylate ester except methyl methacrylate and an acrylate ester, and

0 to 20 % by weight of a vinyl monomer copolymerizable therewith, wherein the total amount of (A) and (B) is 100 parts by weight , and wherein specific viscosity is measured at  $30^{\circ}$ C using Ubbelohde's Viscometer on 0.1 g of polymer dissolved in 100 mL chloroform.